





# Salt


Specification according to EN 1307


|                                        |                  |                                                                                |                           |                    |        |                    |      |      |
|----------------------------------------|------------------|--------------------------------------------------------------------------------|---------------------------|--------------------|--------|--------------------|------|------|
| Type of manufacture                    | ISO 2424         | Tufted 1/10 "                                                                  |                           |                    |        |                    |      |      |
| Aspect                                 | ISO 2424         | Loop pile                                                                      |                           |                    |        |                    |      |      |
| Dye method                             | Solution dyed    |                                                                                |                           |                    |        |                    |      |      |
| Dimension                              | EN ISO 24342     | cm x cm                                                                        | 50 x 50 / 19,68" x 19,68" |                    |        | (20 tiles per box) |      |      |
| Primary backing                        | ISO 2424         | Polyester fleece                                                               |                           |                    |        |                    |      |      |
| Secondary backing                      | ISO 2424         | DESSO ProBase Polyver® - Polyscan®                                             |                           |                    |        |                    |      |      |
| Pile fibre composition                 | ISO 2424         | BCF Polyamide 6 and ECONYL® (ECONYL® is made from 100% regenerated content) ** |                           |                    |        |                    |      |      |
| Total thickness                        | ISO 1765         | mm                                                                             | 7.0                       | inch               | 0.3    |                    |      |      |
| Effective pile thickness               | ISO 1766         | mm                                                                             | 3.9                       | inch               | 0.15   |                    |      |      |
| Total mass                             | ISO 8543         | g/m <sup>2</sup>                                                               | 4100                      | oz/yd <sup>2</sup> | 121.0  |                    |      |      |
| Total pile mass                        | ISO 2424         | g/m <sup>2</sup>                                                               | 680                       | oz/yd <sup>2</sup> | 20.1   |                    |      |      |
| Effective pile mass                    | ISO 8543         | g/m <sup>2</sup>                                                               | 435                       | oz/yd <sup>2</sup> | 12.8   |                    |      |      |
| Pile density                           | ISO 8543         | g/cm <sup>3</sup>                                                              | 0.112                     | lb/in <sup>3</sup> | 0.0040 |                    |      |      |
| Number of tufts                        | ISO 1763         | /dm <sup>2</sup>                                                               | 1540                      | /yd <sup>2</sup>   | 128759 |                    |      |      |
| Stroll test                            | ISO 6356         | kV                                                                             | ≤ 2,0                     |                    |        |                    |      |      |
| Vertical resistance                    | ISO 10965        | Ohm                                                                            | ≤ 1 x 10 <sup>9</sup>     |                    |        |                    |      |      |
| Horizontal resistance                  | ISO 10965        | Ohm                                                                            | -                         |                    |        |                    |      |      |
| Use classification                     | EN 1307          | 33 Commercial - heavy use                                                      |                           |                    |        |                    |      |      |
| Luxury rating                          | EN 1307          | LC 2                                                                           |                           |                    |        |                    |      |      |
| Dimensional stability                  | EN 986           | %                                                                              | ≤ 0,2                     |                    |        |                    |      |      |
| Impact sound reduction ΔL <sub>w</sub> | ISO 10140        | dB                                                                             | 28                        |                    |        |                    |      |      |
| Sound absorption                       | ISO 354          | Freq. Hz                                                                       | 125                       | 250                | 500    | 1000               | 2000 | 4000 |
|                                        |                  | α <sub>s</sub>                                                                 | 0.01                      | 0.01               | 0.08   | 0.20               | 0.33 | 0.38 |
| Noise reduction                        | ISO 354          | α <sub>w</sub>                                                                 | 0.15                      |                    |        |                    |      |      |
| Thermal resistance                     | ISO 8302         | m <sup>2</sup> .K/W                                                            | 0.087                     |                    |        |                    |      |      |
| Flammability                           | EN 13501-1       | Bfl - s1 (loose laid tested)                                                   |                           |                    |        |                    |      |      |
| Prodis - GUT                           | www.pro-dis.info | E0181EA4                                                                       |                           |                    |        |                    |      |      |



 Manufactured by:  
 Tarkett BV  
 Taxandriaweg 15  
 NL - 5142 PA Waalwijk  
 EN 14041  
 0493-CPR-0002


















\*\* ECONYL® is a yarn made from 100% regenerated content. The total % of regenerated content varies per product and per colour. Whether a colour contains ECONYL® and the exact % thereof can be found on our website: [www.tarkett.com](http://www.tarkett.com)

Tarkett's flooring products are to be installed in full accordance with DESSO installation instructions and recognized trade standards. An effective, regular cleaning and maintenance program is vital for retaining a high appearance level. Tarkett's flooring products should only be used as floorcoverings. Note: Tarkett reserves the right to change this specification without prior notice; changes are subject to normal production tolerances. For the latest versions of the technical specifications, visit [www.tarkett.com](http://www.tarkett.com)

EN-20200114